

Preparation of Activated Carbon from the Stem of the Natural Plant Vitex Negundo and Evaluation of Their Physical and Chemical Properties

A. Arun Kumar, T. Chandra Sekaran, K. Riaz Ahamed

Abstract- The powdered activated carbon was prepared from Vitex negundo stem agricultural waste, carbonization was done at 400°C and the chemical activation was carried out using various dehydrating agent such as H₂SO₄, H₃PO₄, ZnCl₂, and KOH and activation process was carried out at 600°C for five hours and allowed cool at room temperature for four hours. The materials were grained and sieved with four different sizes 53μ, 106μ, 300μ and 500μ. The aforesaid particle size 53μ was taken to further studies such as physico-chemical parameters. The characteristic parameters were then compared with commercial activated carbon value. The instrumentation analysis such as Fourier transform infrared (FTIR), scanning electron microscope (SEM) were performed to determine the surface morphology of prepared adsorbent.

Key words: Activated carbon, chemical activation, characterization, FTIR, SEM. BET,

I. INTRODUCTION

The preparation of adsorbents from agricultural waste has potential economic and environmental impacts; it converts unwanted, low-value agricultural waste to useful, high-value adsorbents. Adsorbent are increasingly used in water to remove organic chemicals and metals present in environment [1]. Activated carbon from vegetable material was introduced industrially in the first part of the twentieth century and used in sugar refining [2]. In the US, activated carbon from black ash was found very effective in decolorizing liquids [3]. Agricultural by-products and waste materials used for the production of activated carbons include olive stones [4]. Sawdust[5]. Coconut shells husks[6], palm seed coat[7], rice husks[8]. This study explores new activated carbon from natural plant materials through various processes. The general process to prepare activated carbon is based on carbonizing and activating the carbonaceous precursor material. Activation may be activated physically: a two stage process involving carbonization of the precursor material followed by controlled gasification (steam flow, temperature, heating rate etc) of the char or chemically, in which the precursor material is impregnated with a chemical agent and heated to temperature of 450-700°C[9].

Manuscript Received on June 2014.

A. Arun Kumar, PG and Research Department of Chemistry, Jamal Mohamed College (Autonomous), Tiruchirappalli-620020, Tamil Nadu, India.

T. Chandra Sekaran, PG and Research Department of Chemistry, Jamal Mohamed College (Autonomous), Tiruchirappalli-620020, Tamil Nadu, India.

K. Riaz Ahamed, PG and Research Department of Chemistry, Jamal Mohamed College (Autonomous), Tiruchirappalli-620020, Tamil Nadu, India.

In chemical activation several type of chemicals are used as the activating agent including ZnCl₂, H₃PO₄ and KOH having different properties. Hayashi and coworkers [10] found that the greatest specific surface area of activated carbons was obtained at the carbonization temperature of 600°C with ZnCl₂ and H₃PO₄ activation. The industrials effluent treated by waste water treatment plants contain large amounts of organic matter and pollutants including metal such as Cu, Zn, Cd, and Pb etc, the uptake of metals in pollution control[11]. Activated carbon is an efficient and versatile adsorbent for purification of water, air and may chemical and natural products [12]. To enhance the capacity of activated carbon to adsorb cations, many functional/surface modification[13] methods have been introduced. These include chemical or physical treatment [14-16] and surface modification [17-22]. The aim of this paper is to produce activated carbon from Vitex negundo stem waste and characterize the carbon. The prepared carbon sample values are also compared with commercial activated carbon [23].

II. MATERIALS AND METHODS

2.1. Chemicals

Sulphuric acid, Phosphoric acid, Zinc chloride, Potassium hydroxide and all reagents used in this study were procured from Merck, India. Double distilled water used for all the Physico-chemical characterization work.

2.2. Preparation of Activated Carbon

The Vitex negundo plant was collected from an agricultural waste in Ariyalur district, Eravangudi village, Tamil Nadu, India. The precursor was washed with distilled water to remove impurities, cut into small pieces (2.5cm), dried in sunlight. Activation processes were carried out by physical and chemical activation.

- I. In physical activation, the precursor sample was heated at high temperature at 600°C for five hours and then cooled, grained, sieved and stored in air tight container, named as VNC.
- II. Chemical activation is a two step process, in chemical activation the precursor samples were soaked in dehydrating chemicals such as H₂SO₄(50%), H₃PO₄(50%), ZnCl₂(50%) and KOH(50%) for 24 hours. So, that solution gets well adsorbed for a period of 24 hour at the end of 24 hours excess solution was decanted off and dried in hot air oven maintained at 110°C for 4 hours. Then the chemically dipped precursor sample was placed in muffle furnace.



The carbonization process was carried out at 400⁰C and the carbonized samples were made to activate at 600⁰C for 5 hours. All process was carried out in absence of air.

The activated carbon sample was washed with plenty of double distilled water to remove excess acids. During the washing process, 0.1M HCl or 0.1 M NaOH was used until the pH of the washing solution reached to 6-7 and dried at 110⁰C. The dried material was grained and sieved with different sized meshes (0-53μ, 53-106μ, 106-300μ, and 300-500μ) and named as VNC-1(H₂SO₄), VNC-2(H₃PO₄), VNC-3(ZnCl₂) and VNC-4(KOH). The different sized carbon sample was stored in air tight plastic container to further use.

2.3. Experimental Techniques

The Physico-Chemical characterization was carried out for prepared carbon samples to identify the nature and properties for the prepared adsorbent. The samples were also subjected to FTIR to elaborate the functional groups present in the surface of the carbon samples. The various characteristic parameters such as moisture content, Bulk density, ash content, matter soluble in acid, matter soluble in water, loss on ignition, pH, iron content, iodine number and surface area. The experiment was followed by Hassler procedure from this characteristics work [24]. We can conclude the nature of an adsorbent and results was listed in table-1.

2.4. Result and Discussion

Bulk density of carbons obtained from all the materials show that carbon VNC1 (0.41g/ml) and VNC-3(0.50 g/ml). Higher bulk density due to its high fiber content, VNC-2(0.36 g/ml) and VNC-4(0.36 g/ml) has the lower bulk density and compared to a VNC (0.39 g/ml) carbon has the

lower bulk density and commercial activated carbon (CAC) has the higher bulk density. The moisture content is found to be VNC-1 is the 0.51% and is comparatively very less to other carbon (VNC, VNC-2, VNC-3, VNC-4 and CAC) and hence the experimental carbon is found to have more surface area for adsorption. Ash contents for all carbon were found to be very low thereby increasing the fixed carbon content for the carbon obtained from prepared samples. The characterization studies on iodine number VNC-1 possess high iodine number of 360 and it is compared with commercial activated carbon (CAC) has the lower iodine number of 200.36 indicated in (Table-1). Iron content is almost low for all the carbons. This level of iron content will not affect the effluent water without the problem of iron leaching into treated water. . The surface area was determined by BET method using nitrogen as the adsorbent at liquid nitrogen temperature. The BET surface area value VNC1 (H₂SO₄) is the 319 shown in Fig.1. Compared with commercial activated carbon 296 (CAC) has the high surface area value is the VNC1. This has been further confirmed by the surface morphology studies using SEM shown in Fig. 6 is the VNC1 (H₂SO₄) chemical activation from which it is evident that VNC1 (H₂SO₄) has a significantly porous structure. However, it is seen from figure.7 that has nearly disappeared the after adsorption of Pb(II). The FT-IR spectrum shown in Fig. 2 to 6 reveals that the activated carbon contains a number of functional groups such as, -COOH, O-H, C-H, C-O, C=O, N-H, amides, monosubstituted aromatic structure *etc.* From the characteristics parameter it proves that the carbon prepared by H₂SO₄ (VNC-1) process found high in a vast margin when compared to other carbons because of high charring power of H₂SO₄, thus the H₂SO₄ activated carbon process showed better result.

Table-1: Comparison between the prepared activated carbon and commercial activated carbon

Parameters	Units	VNC	VNC-1	VNC-2	VNC-3	VNC-4	CAC
Ash content	%	2.79	5.32	11.0	9.96	29.80	17.1
Bulk density	g/ml	0.39	0.41	0.36	0.50	0.36	0.66
Iron content	%	0.6	-	-	0.16	-	-
Iodine number		279	360	359	343	291	200.36
Loss on ignition	%	89.42	91.61	92.39	89.29	93.96	97.09
Matter soluble in acid	%	0.27	0.89	2.89	3.09	4.03	4.58
Matter soluble in water	%	2.09	0.49	0.99	0.52	2.20	1.55
Moisture content	%	1.40	0.51	0.47	0.74	1.38	16.67
pH		5.7	4.2	1.9	7.0	12.2	7.0



Figure: 1 BET Surface area for VNC-1




Figure:2.FTIR spectrum of VNC Carbon




Figure:3.FTIR Spectrum of VNC-1 Carbon




Figure:4.FTIR Spectrum of VNC-2 Carbon




Figure:5.FTIR Spectrum of VNC-3 Carbon




Figure:6.FTIR Spectrum of VNC-4 Carbon





Fig.7. (a),(b) and (c) SEM micrograph of the VNC-1 before, after adsorption and EDAX of Pb(II)

ACKNOWLEDGMENTS

The authors thank the management and principal of Jamal Mohamed College (Autonomous), Tiruchirappalli, Tamil Nadu for their support and encouragement.

REFERENCES

1. Fawzi, A and Banat S. (2000). Biosorption of phenol by chicken feathers, Environ Engg and policy. 86 :85-90
2. Bansal. RC, Donnet. JB, Stoeckli. F. Active carbon (Marcel dekker, New York) (1968)
3. Manteu. CL, carbon and graphite hand work(John Willey & Son's, New York) (1968)
4. Lopez-Gonzalez. DJ. (1984) high temperature adsorption of hydrocarbons by activated carbons prepared from olive stones, Adv Sci Technol.1: 103-109
5. Srinivasan K., Balasubramanian. N & Ramakrishna.TV. (1988) studies on chromium removal by rice husk carbon, Indian J Environ Hlth.30 :376-387
6. Morais LC., Goncalves EP., Vasconcelos LT& Beca CG., (2000). reactive dyes removal from waste waters by adsorption on eucalyptus bark- adsorption equilibria, Environ Technol. 21:577-583
7. XUX, Shiv&Sun G., (1997) sunflower stalks as adsorbents for colour removal from textile waste water, Indian Engg Chem Res. 36:808-813
8. Rengaraj S, Banumathi A, murugesan B., (1999). Preparation and characterization of activated carbon from Agricultural wastes, Indian J. chem. Technol. 6: 1-4.
9. Ahmedna M, Marshall W.E. and Rao R.M., (2000). Granular activated carbon from agricultural by-products: preparation properties and application in cane sugar refining bulletin of louisiana state university agricultural centre.54
10. Hayashi. J, Kazehaya. A, Muroyama. K, and Watkinson. A.P.,(2000). "Preparation of activated carbon from lignin by chemical activation", carbon.38:1873-1878
11. Guibaud.G, Hullebusch E.V and Bordas F., (2006). Lead and cadmium biosorption by extracellular polymeric substances (EPS) extracted from activated sludges: pH-sorption edge tests and mathematical equilibrium modeling. Chemosphere.4(11): 1955-1962
12. Malik R., Ramteke D.S and Wate S.R., (2007). Adsorption of malachite green on groundnut shell waste powdered activated carbon. Waste manage.27:1129-1138
13. Mu G.N, Tang L.B, (2002). Adsorption of Cd(II) ion and its complex compounds from solution on the surface of charcoal treated with an oxidation -negative ionizing method, J. Colloid Interface Sci.247:504-506
14. Yossef A.M, El-nabrawy.Th, Samra S.E., (2004). Sorption properties of chemically activated carbons:1, sorption of cadmium(II) ions, colloids surf.A. 235:153-163
15. Nadeem. M, Mahmood A,Shahid S.A, Shah S.S, Khalid A.M, McKay G., (2006). Sorption of lead from aqueous solution by chemically modified carbon adsorbents. J.Hazard.mater.B.138:604-613
16. Amuda O.S, Giwa A.A, Bello I.A., (2007). Removal of heavy metal from industrial waste water using modified activated coconut shell carbon, Biochem. Eng.J.36:174-181
17. Yang L, Chen J.P., (2007). Modification of activated carbon by polyaniline for enhanced adsorption of aqueous arsenate, Ind.Eng.Chem.Res.46:2133-2140
18. Monser L., Adhoum N., (2002). Modified activated carbon for the removal of copper, zinc, chromium and cyanide from waste water, sep.purif.Technol.26:137-146
19. Basar C.A., Karagunduz A., Keskinler B., Cakici A., (2003). Effect of presence of ions on surface characteristics of surfactant modified powdered activated carbon(PAC) App.surf.sci.218:169-174
20. Choi H.-D., Cho J.-M., Baek K., Yang J.-S., Lee J.-Y. (2009). Influence of cationic surfactant on adsorption of Cr(VI) onto activated carbon, J.Hazard.Mater.161:1565-1568
21. Hong H.-J, Kim H., Baek K., Yang J.-W. (2008). Removal of arsenate, chromate and ferricyanide by cationic surfactant modified powdered activated carbon,Desalination.223:221-228
22. Rengaraj.s.,Seung.Hyeon Moon, Sivabalan .R *et.al.*,(2002). Agricultural solid waste For the removal of organics: Adsorption of phenol from water and waste water by palm seed coat Activated carbon. Waste management.22:543-548.
23. Ekpete.O.A, Horsfall M. JNR,(2011). Preparation and Characterization of Activated Carbon derived from Fluted Pumpkin Stem Waste (*Telfairia*



III. CONCLUSION

The results obtained from the present study suggest the possible use of a widely available and environmental friendly material as an adsorbent for water treatment. *Vitex negundo* stem powdered chemically activated H_2SO_4 shows best for the removal of heavy metals.

Preparation of Activated Carbon from the Stem of the Natural Plant *Vitex Negundo* and Evaluation of Their Physical and Chemical Properties

occidentalis Hook F) Res.J.Chem.Sci.1(3)

24. Hassler J.W., Purification with Activated Carbon, Chemical Publishing Co. Inc., New York, edn. 2 (1974).

AUTHORS PROFILE



A. Arun Kumar, Research Scholar, PG and Research Department of Chemistry, Jamal Mohamed College (Autonomous), Affiliated to the Bharathidasan University, Tiruchirappalli-620020, Tamil Nadu, India



T. Chandra Sekaran, Research Scholar, PG and Research Department of Chemistry, Jamal Mohamed College (Autonomous), Affiliated to the Bharathidasan University, Tiruchirappalli-620020, Tamil Nadu, India.



Dr. K. Riaz Ahamed, Assistant Professor, PG and Research Department of Chemistry, Jamal Mohamed College (Autonomous), Affiliated to the Bharathidasan University, Tiruchirappalli – 620020, Tamil Nadu, India.