

Tool Condition Monitoring in Hard Turning of Inconel 718 by using Vibration Technique

D. Kondala Rao, Kolla Srinivas

Abstract: In various machining processes, the vibration signals are studied for tool condition monitoring often referred as wear monitoring. It is essential to overcome unpredicted machining trouble and to improvise the efficiency of the machine. Tool wear is a vital problem in materials such as nickel based alloys as they have high hardness ranges. Though they have high hardness, a nickel based alloy Inconel 718 with varying HRC (51, 53, and 55), is opted as work material for hard turning process in this work. Uncoated and coated carbide tools are employed as cutting tools. Taguchi's L9 orthogonal array is considered by taking hardness, speed, feed and depth of cut as four input parameters, the number of experiments and the combinations of parameters for every run is obtained. The vibration signals are recorded at various stages of cutting, till the tool failure is observed. Taking this vibration signal data as input to ANOVA and Grey relation analysis (GRA) which categorizes the optimal and utmost dominant features such as Root Mean Square (RMS), Crest Factor (CF), Skewness (Sk), Kurtosis (Ku), Absolute Deviation (AD), Mean, Standard Deviation (SD), Variance, peak, Frequency and Time in the tool wear process.

Keywords :Hard turning, Tool condition Monitoring (TCM), Dominant features, Vibration signals, GRA, ANOVA.

I. INTRODUCTION

In aerospace applications Nickel-based super alloys are widely used due to their magnificent corrosion resistance and mechanical properties maintained at high temperature. Especially Machining of Ni based alloys is still a challenge in dry machining. Super alloys characteristics like high temperature, tensile strength, shear strength, strain hardening, decrease in thermal conductivity, built up edge formation and the occurrence of abrasive particles in their microstructures etc. are induce high thermo-mechanical loads at the tool-chip interface resulting in important wear of the tool [1]. Cemented carbide inserts were not suitable to machine Ni based alloys at high speed since they cannot survive the conditions of acute high temperature and stress in the cutting zone. In general, the suggested range of cutting speeds up to 30 m/min for uncoated tools and up to 100 m/min when machining Ni-based alloys using cemented carbide inserts properly coated [2]. Ceramic tools have been used gradually more In metal-cutting processes tool wear is a complex phenomenon occurring in various ways.

Revised Manuscript Received on September 03, 2019

* Correspondence Author

D.Kondala Rao*, Research scholar, Dept. of Mechanical Engg., University college of engineering & Technology, Acharya Nagarjuna University, Guntur, Andhra Pradesh, India. Email: kondalmech@gmail.com

Kolla Srinivas, Professor, Dept. of Mechanical Engg., R.V.R. & J.C. College of Engineering, Guntur, Andhra Pradesh, India.

Email: dr.kollasrinivas@gmail.com

Normally, the surface finish is mainly affected by a worn tool and therefore there is a necessity to build up tool condition monitoring (TCM) systems that alert the machinist to the tool wear state, thereby avoiding adverse effects [3]. TCM systems that were improved in the past are comprehensively revised in a number of articles. A good quality cutting TCM system [4] should be characterized by (i) gradual tool wear (crater and flank) caused by abrasion due to friction between cutting tool and work piece (flank wear) and cutting tool and chip (crater wear), (ii) tool chipping (cutting edge breakage) and (iii) fast recognition of impact or collisions, (i.e., unwanted movement between tool and work piece) Tool wear sensing methods are generally classified into two types: direct and indirect tool wear monitoring methods The direct methods can be applied when cutting tools are not in contact with the work piece [5] like radioactive, microscope, camera vision and so on. These indirect methods can be developed to an industrial problem, but they have a lower sensitivity than direct methods However, a problem in TCM system is selection of proper sensor and its location. The sensors have to be placed as close to the tool tip being monitored. It is exciting to note that an indirect TCM system [6] consists of four steps: (i) collection of data in signals from sensors such as cutting force, vibration, temperature, acoustic emission and/or motor current, (ii) features extraction from the signals, (iii) tool wear estimation using pattern recognition, fuzzy logic, neural networks, or regression analysis, and (iv) implement of an adaptive system to control the machining process based on data from the sensors. The present work is going to be use vibration indirect method.

II. VIBRATION SIGNATURE

vibrations happen as a result of rubbing action between the work piece and chip against the tool in turning operation. If the tool wear increases, variation will be observed in tool signature provided by these vibrations. The vibration free cutting processes greatly effects the operation of machine tool in terms of its performance. The increase of deterioration rate and inaccuracies with respect to time can be certainly measured by vibration monitoring in a machine tool. In general, these vibration signals can be recorded by means of a sensing device named accelerometer. These vibration monitoring techniques [9, 10–14] are reviewed by the researchers Dan and Mathew [8] as more economical, efficient and practical, also stated the merits and demerits. Teti et al. [15] also described various vibration sensing techniques [16, 17] to monitor flank wear in their entire research work conducted on machine monitoring techniques. Rajesh and Narayanan Namboothiri [18] conducted nonlinear time series analysis by

Tool Condition Monitoring in Hard Turning of Inconel 718 by using Vibration Technique

examining the vibration signals which are occurred all through the cutting process. Ding and He [19] also researched on tool condition monitoring information attained from cutting tool vibration signals, Acoustic Emission signals, servo motor current signals, spindle and microscopy technique, based on which they developed a model among tool wear states and reliability. The developed model provides more effective assessment for tool reliability. Quantifying the vibration signal is easy but the recorded signals are significantly dependent on all the cutting conditions, material of the work piece and machine structure.

III. METHODOLOGY

The proposed methods were tested using a single point cutting tool in an industrial high-speed turning lathe machine Lokesh TL200. Vibration measurements are noted over a period using vibration sensor. During the measuring period, the tool is periodically removed from the chuck, and tool wear is measured using 'Tool Makers microscope'. This produced a baseline time plot of actual tool wear versus time. Eleven features, generally used for machinery monitoring in industries, are calculated from the measured vibration data. ANOVA was applied to observe the most contributing feature among the eleven features. The GRA method was then used to observe the optimal feature values with the help of Artificial Neural network (ANN).

IV. EXPERIMENTAL WORK

A. Workpiece material, cutting tool and measurement of flank wear: The present work is completed on CNC lathe Lokesh TL250. All the turning operations are conducted on a round bar (50 mm dia and 10Kg weight) of Inconel 718, hardness (51,53 and 55HRC) with uncoated cemented carbide insert (TNMG160408 MS SW05) and coated cemented carbide insert (TNMG 160408 MS PR1305 with tool holder MTJNL 2020K16 without cutting fluid for this research work.

The flank wear of three tool inserts is determined using Tool maker's microscope (LT-24) by Elshaddai Engineering Equipment's. The specifications of the microscope include a Magnification of 30X with X-Y movement on ball bearing slides, 25mm graduated micrometers and least count of 0.001mm. In this work, for every 120mm length of cut the tool flank wear is measured for each workpiece.

B. Cutting conditions:

The present work focusses on the assessment of extracted dominant features of flank wear with uncoated and coated inserts with dry machining. Experiments are conducted taking four cutting parameters (speed, feed rate, depth of cut and hardness) into account with three levels for every parameter. The details are clearly mentioned in the Table 1.

C. Measurement and processing of vibration signals during cutting: By means of Taguchi's L9 orthogonal array the number of experiments and the combinations of parameters for every run is obtained. The vibration signals are recorded at different stages of cutting, till the tool failure is observed.

The vibration signals were measured using a Kistler8704B100M1uni-axial accelerometer have been

mounted on top of the tool holder with magnetic clamp (Kistler 8443B), and placed possibly near to the tool insert. The frequency range of accelerometer is 1 Hz to 10 kHz and the sensitivity of the accelerometer is 50 mV/g ($\pm 5\%$) The accelerometer detected the vibration signals in z-direction. In the end the trained signal is directed to laptop with LABVIEW software in order to display and storage. The vibration signal data is collected and stored in an excel file, can be processed and analyzed later.

Table 1 Experimental parameters and their levels

Levels of the experimental factors	parameters			
	Speed, N [rpm]	Feed rate, f [mm/rev]	Depth of cut, d [mm]	Hardness [HRC]
1	50	0.05	0.1 5	51
2	65	0.07 5	0.2	53
3	80	0.1	0.25	55

V. RESULTS AND DISCUSSION

The nine experimental runs were performed based on the combinations from Table 1 with each experimental run carried for a length of 120 mm. All the operations on CNC were performed using numerical control part programming. By using high resolution Tool maker's microscope, the tool flank wear is measured. The tool wear obtained from tool maker's microscope were given in the table 2. The uncoated carbide cutting tool vibration signals of Fig.1 have been captured for all the combinations cited in Table 2 (similarly coated carbide tool signals also captured) cutting speed, feed, depth of cut and hardness of the material.

Various Features were calculated by using Lab View software and MATLAB for each and every signals collected by accelerometer. These features and corresponding outputs (tool wear, surface roughness and temperature) trained with Neural Network by considering the parameters and got high accuracy of 98%. After obtaining satisfactory relation between features and outputs in neural network training, we simulated the results for different variations in the features and obtained the outputs which was presented in the following figures 2 to 7.

A. GREY RELATION ANALYSIS FOR VIBRATION

The average grey relational grade of each factor at each level was obtained by taking the average of the grey relational grades for the required factor at the required



level. The best level for each factor was obtained based on 'higher is better' characteristic. The dominant feature was attained by taking the extreme value of all factors. Fig.8 shows the sequence of dominant features. AD is the manipulating feature of tool wear for two tool inserts and values are maximum for coated carbide tool insert, minimum for uncoated carbide tool insert.

Table 2 Manual Tool Wear for uncoated and coated inserts from Tool maker's microscope

EXP NO	SPEED [m/min]	FEED [mm/rev]	DOC [mm]	HARDNESS [HRC]	Tool Wear(uncoated) [mm]	Tool Wear(coated) [mm]
1	1	1	1	1	0.245	0.19
2	1	2	2	2	0.185	0.175
3	1	3	3	3	0.2	0.16
4	2	1	2	3	0.2	0.19
5	2	2	3	1	0.2	0.145
6	2	3	1	2	0.22	0.14
7	3	1	3	2	0.21	0.19
8	3	2	1	3	0.175	0.17
9	3	3	2	1	0.2	0.14




Fig.1 vibration signal captured in turning




Fig. 2 Performance graph for vibration signals(coated)




Fig. 3 Training state graph for vibration signal(coated)




Fig.4 Regression graph for vibration signals(coated)




Fig. 5 Performance graph for vibration signals (uncoated)




Fig.6 Training state graph for vibration signal (uncoated)

B. ANALYSIS OF VARIANCE(ANOVA)

ANOVA examines the null proposition that the population means of every level are equal, versus the alternate hypothesis that minimum one of the level means are not equal. This is obtained by splitting the overall changeability of grey relational grades. It is stately by the sum of squared deviations from the total mean of grey relational grade, into contributions from every turning parameters and errors. In addition, the F-test is used to determine what turning factors have a key effect on the output responses. Commonly, the change of turning parameter has main effect on the output response when the F- value is higher. Fig.9 shows sequence of percentage contribution of each feature. Also in ANOVA, AD is found to be the utmost manipulating feature of tool wear. For both coated and uncoated tools, AD is the most dominant feature even after comparing with GRA.




Fig.7 Regression Graph for vibration signals (uncoated)




Fig 8. Level of sequence of features




Fig 9. Percentage contribution of features

VI. CONCLUSIONS

From the present research work it can be concluded that

- Using both the methods Taguchi and GRA dominant features are observed to find the tool wear in TCM.
- Various Features are assessed from the LAB VIEW and MAT LAB software.
- In MATLAB, a neural network technique is developed to train the remaining features in order to get the relation between tool wear and the dominant features, around 98 % accuracy is observed.
- Tool wear is calculated by Simulating Neural Network, dominant features considered as input data from L27 Taguchi orthogonal array.
- The Simulated data is analyzed by Grey relational method and attained grey grade, which is used to observe the dominant feature for the TCM.
- Absolute Deviation is found to be the most dominant feature for vibration signal.
- ANOVA analysis is accepted for the simulated data and grey codes, recognized that the same feature is obtained for Vibration signal.

ACKNOWLEDGEMENT

The authors gratefully acknowledge the funding agency, the University Grants Commission (UGC) of the Government of India [FileNo:42-895/2013(SR)], for providing financial support, to carry out the research work. The authors also appreciate the support of 'Incubation Centre', Department of Mechanical Engineering, R.V.R&J.C. College of Engineering (Autonomous), Guntur, for providing vital support in conducting the experiments and completing the work.

REFERENCES

1. E.O.Ezugwu, vol.45, Issue12-13, pp.1353-1367, 2005.
2. S.Olovsio, L.Nyborg, vol.282-283,2012.
3. Xiaozhi Chen, Beizhi Li, vol.33, pp.968-976, 2007.
4. Scheffer C,Kratz H,Heyns PS,Klocke F, vol.43,pp.973-985, 2003.
5. S.Kurada, C.Bradley Computers in Industry,vol34(1), Oct.1997,pp.55-72.

6. Sunilkumar K, L Vijayaraghavan L, R Krishnamurthy, IEEE: 1995, pp.25-29.
7. Milind A Siddhpura, Arti M Siddhpura, SK Bhawe, Int Conference on frontiers in design and Manufacturing Engineering (ICDM), Coimatore (India), 2008.
8. Li Dan, J.Mathew, vol.30, Issue.4, pp.579-598, 1990.
9. S.B. Rao, vol.108, Issue.3, pp.183-190, 1986..
10. E.J. Weller, H.M. Schrier, Bjom Weichbrodt, vol.91, Issue.3, , pp.525-534, 1969.
11. A.Del Taglia, S.Portunato, P.Toni. Proceedings of 17th International MTDR conference, vol.7, pp.141-148, 1976.
12. S.M.Pandit, S.Kashou, vol.104, Issue.3, pp.217-223, 1982.
13. S.M.Pandit, S.Kashou, vol.84, Issue.1, pp.65-79,1983.
14. C.Y.JiangY, Z.ZhangH, J.Xu, CIRP Annals, vol.36, Issue1,pp.45-48, 1987.
15. Teti R, Jemiel naik K, O Doneell G, Dornfeld D, vol.59 , Issue2, pp.717-739, 2010.
16. Ming-Chvuan Lu, Elijah Kannatey-Asibu, vol.124, Issue.4, pp.799-808, 2002.
17. F.J. Alonso, D.R. Salgadovol.22, Issue.3,pp.735-748. 2008.
18. V.G. Rajesh, V.N. Narayana Namboothri, vol.14, Issue.9, pp.913-919, 2010.
19. Feng Ding, Zhengjia He, vol..57, Issue.5-8, pp.565-574, 2011.