

# Road Construction by using Rolled Compacted Concrete

Muhammad Khidre Musa, Hazar M. Nassrullah

**Abstract :** Rolled compacted concrete (RCC) is important of newly technique in construction of pavement. that can be employed in low traffic or high trafficked roads.

Due to its inexpensive, quick creation, durable and low maintenance RCC is becoming more commonly gradually. If the UHPC compared to normal concrete has some privilege such as plenty stability and supreme permanence however the utilization of it is restricted owing to its expensiveness and minimal costs for design.. Its constancy leads to its stay persistent when subjected to vibratory compacter, since it has sufficient wetting so it causes permit enough mixing and repartition of paste without segregation. Fly ash, silica fume and some admixture can be utilized to concrete to decrease the quantity of water and generate high arid mixture.

**Key Words:** RCC, pavement, fly ash, silica fume, slag

## I. INTRODUCTION

RCC assign to pavement of concrete that is spread and by using hefty apparatus machine it Compacted in a procedure alike to that apply for asphalt roads. According to the ACI code the roller compacted concrete (RCC) can be describe as a comparatively cementitious materials, hard mixing of water and aggregates, that by employing vibratory rollers it can be compacted by [1]. RCC its used for first time in the 1970s, RCC has a confirmed that successfully can be employed in pavement usage. RCCP generally carry out well cold weather and by using of heavy machines. And it can be used in more cost-effective pavements for very ordinary road and operations similar shoulders of highway, light traffic roads, regional streets, and large parking zones [2].

RCC in fresh state is harder than classic no-slump normal concrete. Its constancy leads to its stay persistent when subjected to vibratory compacter, since it has sufficient wetting so it causes permit enough mixing and repartition of paste without segregation [3].

• More modern advancement involve the employed of RCCP in the civic pavement field. Small preservation ways, residentiary avenues, and main highways demonstrate the large public usage. Other applications contain RCC coated with asphalt, heavy vehicles path, construction of shoulder for highway and approach lanes for junction [4].

**Revised Manuscript Received on September 05, 2019.**

**Muhammad Khidre Musa**, Musa.,Ph.D. Students, Civil Engineering Department/ Near East University/ North Cyprus, Nicosia, Via Mersin 10, Turkey, mmkidre@gmail.com

**Hazar M. Nassrullah**, department, Name of the affiliated College or University/Industry, City, Country. Email: xyz2@blueeyesintelligence.org

The utilization of RCCP in some countries such as India, Australia, ...etc, for In the state of Indiana, the fondness in the employing of RCCP for regional ways and avenues has enhancement, and many states and locations have commenced to create RCCP. there are some deeds and costs that illustrate the knowledge and specialized data concerning to RCCP, feasible advisor that can be employed by local organization to arrangement, plan, and manufacture the RCCP. For purpose to provide sufficient instructions and guidance that need for practical [5].

Many number of dams are constructed by utilization of RCC technology, but its application in road building is increasing daily. And it is a significant and important alternative for local administration transportation system because it supply more economical transportation because it contain low binder, reinforcement is not required, longer cuts for jointing distance, not required to molding, comfort and quick for emergency traffic service, and it can be paved and compacted by ordinary machine that can be used for asphalt pavement

## II. FUNDAMENTAL RCC PAVEMENT ESTABLISHMENT

RCCP point out to concrete pavement that is insert, paved and compacted with same procedure of bituminous asphalt roads. The proficiency of RCCP is alike to normal rigid roads that it has extreme permanence and high strength. This category of pavement patulous to vehicles movement more quicker than ordinary concrete roads. This sort of concrete is competent routes with small speediness vehicles and route that necessary to be repair and employing at early time [5].

## III. UTILIZATION OF ROLLER-COMPACTED CONCRETE (RCC)

According to the materials that used for RCC is a category of concrete that, with some difference characteristic, the compound and mixing, but vary from differs from traditional concrete by technical its arrangement and paving that it used roller for compacting instead in lieu of, of vibrant [7]. The requisition for RCC usage for special and common work recently is enchantment. RCC can be utilized particularly in building for new dam and renovation of extant dams, also it may be employed for the projects that mentioned below:

- Roads and its shoulders
- Feasibility of Parking and big storage and harbor
- Building and dams

# Road Construction by using Rolled Compacted Concrete

## A. RCC Dams

The earliest usage of building dam by RCC's history return to the 1960s, that RCC was employed for a recent dam manufacture. The major economic privilege due to hereunder specifications of RCC dams[8]:

- a. **Quick in installation and placing n:** Big quantity of (small or more paste) concrete can comfortably be paved with hefty machine, therefore the time for building these dams become shortening
- b. **Economic RCC:** The price of small paste heap concrete is desirable; to decrease the generation heat a large quantity of cement is often substitute by regionally existing pozzolanic substance such as slag or fly ash.
- c. **Construction of wastewair for dam frame:** Because of the inclination of the downstream face the spillway can immediately be unify into the dam frame that supports to incorporate high storms and which are in necessity of big wasteweirs.
- d. **Heat of hydration :** If heat of hydration wastage is taking into consider the RCC is so desirable which is often remnant a fundamental matter for mass concreting composition

## B. RCC Pavements (RCCP)

RCC for pavements possess almost more quantity of cementitious substance as mélange of RCC for dams. RCC pavement is more faster to build than normal concrete pavement. RCC pavements no need dowels ,joints,steel reinforcement , dowels , or moldings. RCC pavement is more powerful and stable and persistent than bituminous asphalt road. It will not break and prevent of pathole under high vehicles loads, or pushe or rupture due to breaking or turning of running apparatus and machines It retain Its hardness when subjected to heat begotten by hot weather or material stockpiled on RCC floors [9]

## C. In maintenance and renovation works

RCC is usually utilized to maintain defective overflow framework, to retain the earthworks and heaps pending overtopping and to creation delimiter and buffer for fortify an crenellate large dams.

## IV. DESIGN INSTRUCTIONS FOR RCC PAVEMENTS

The whole of methods that applied for the design to portland cement concrete pavements involving the, ACI Committee 325 design guides (ACI 2002) , ACPA design guide (ACPA 2002), AASHTO 1993 design procedure (AASHTO 1994), can be employed to the create and advise of RCCP. The StreetPave (PCA 1984 and the ACPA 2006) PCA/RCC-Pave (PCA 2001) programming for computer are common design tools for RCCP Due to their performance and plainness. PCA/RCC-Pave is appropriate for the perform and lay out of the hefty function related to manufacturing pavements, that have uncomplicated traffic policy. Street Pave is proper for the design of the pavements that used for medley transport traffic. The work of Delatte (2004) and PCA (2009)) can be utilizable for the design of composed pavements. [10].

## V. DESIGN PROCESS

The undermentioned four criteria are should be considered in the design stepsof RCCP and should be defined previously e trying to compute and fine the thickness of pavement [11]:

1. elastic modulus of the RCC and Strength
2. Traffic classification and mean diurnal truck traffic (ADTT)
3. Response subgrade modulus
4. Situation support Edging

While these criterion have been funded, the suitable RCCP thickness can be compute `by utilizing the design steps of RCCP

1. Pavement Design
2. consider RCC characteristic
3. assessment traffic status: Street classification and traffic
4. appraisalment base situation: subgrade and subbase
5. Determine the thickness of RCCP [5]

## VI. ATTRIBUTES RCC

Commonly , flexural strength (frup) is more significant in production and lay outing concrete pavement because it determine the fortification beneath a different kind of forced that may applied to the pavement in the the site. The relation between the flexural and compressive strengths and compressive of RCC is same to that of ordinary concrete. Next concrete character that should be considered in the in design of pavement is the elastic modulus (E). The elastic modulus, of concrete is a indicate of the amount of material deflections. The elastic modulus of RCC may be alike to or some greater than that of normal concrete with same quantity of cement . The mechanical attributes are relay on many moods similar water and cement content, amount of aggregate, and compaction, a 4.5 mps of flexural strength can be employed the rapture modulus for a usual mixing of RCC. [12].

## VII. ENGINEERING CHARACTERISTIC OF RCC

### A. Strength

The strength virtues of RCC relay on the quantity of cementitious substance, w/cm proportion, aggregate modality, and concrete compaction. Commonly this type of concrete have flexural strengths and compressive similar to the ordinary concrete paving.

### B. Compressive Strength

This typed strength of RCC is alike to that of normal concrete, commonly vary from 28 to 41 MPa. Some time the compressive strengths have reached higher than (48 MPa. T0 help the concert to attain high amount of compressive strength use small w/cm and condensed small w/cm aggregate utilized for production mixture of RCC. This gives minimum pore cement mixture that also lead to the increase compressive strength.

### C. Flexural Strength

modulus of rupture is depending up on to the compressive strength and density . In perfectly create RCC roads, the aggregates are densely compressed and reduce the progress of cracking by fatigue. The paste density ste and the bond strength to the aggregate grain are supreme because of its small water/cement proportion. As a consequence, the modulus of rupture of RCC, rely on the mixture composition and properties, is typically high—value from (3.5 to 7 MPa). There is no more knowledge existing on the flexural strength of RCC due to hardness of acquiring cutting beam samples from real paving in the fields and the inexistence of a systematize experimental mechanism for constructing beams in the site and lab.

### D. Fatigue

When a material is exposing to frequentative loading fatigue defeat happens. Since the stress induced by a lone force is not larger than the substance resistance ,recur of these loads will corrode and damaging on the substances gradually and at the end cause in fatigue defeat. Because the flexural are climacteric stresses in RCC pavements, fatigue owing to stresses in shape of flexural is utilized for finding for thickness of RCC. Stress proportion, as employed in fatigue relation, is the proportional of flexural stress to flexural resistance. For example, if a force applied by wheel causes a flexural stress of 2.70MPa and RCC flexural resistance is 4.42 MPa), then the strees ratio is 0.61 [13].

### E. Bond Resistance

Critical engineering exclusivity of RCC is bond strength. Bond strength distinguish either RCC pavements built in multifold lifts will acts as a one substrate or as partly stick or not stick lifts. The load transfer valency of partly stick or not stick lifts is smaller than that of bonded lifts of equivalent whole depth. Commonly, sufficient bonding resistance is attain when pavement layers are paved during an hour of each other, but installation may required to be faster in hot climate. To investigation for bonding strength the cores should be taken. Information from experiment segment showed that enough junction bond strength can be obtained for correctly built RCC installation. Nevertheless , the information also indicate that bond stamina progress alongside the margin of lengthwise building joints may be smaller than the stick stamina in internal positions[3]

### F. Freeze-Thaw resistance

freeze-thaw (F-T) repetition are two kinds of detrimental that typically exposed to RCC pavements : interir cracking and exterior scaling. Since these kinds of distortion may happen in the same time , they are distinguished and self-determining occurrence. If the RCC concrete possesses considerable humidity, F-T sequence can create interior l cracking, that smaller the dynamic internal elastic modulus and consequence in expansion. Exterior scaling also happens during F-T repetitions while high quantity of humidity influenced on the concrete. This procedure deteriorate in the availability of deicing salts .mixture of

RCC mixes shouldt be construct and lay out to stand out against both kinds of assault due to F-T cycles. Site proficiency researches have showed that RCC has carry out well in rough climatic status. researches in the Canada and USA demonstrate that RCC mixes, both air entrained or not, have executed well for more than thirty years. According to some studies on 34 RCC pavements in USA and Canada For air entrained RCC, have proven that RCC persistence fot F-T reptleion significantly increased by air entraining admixtures [14].

### G. Shrinkage

Any considerable variation in mass of RCC paving occurring by drying shrinkage. although, the volume alteration related with drying contraction is commonly smaller than that normal mixing concrete owing to the smaller existence of water in RCC. Therefore, a smaller quantityof cement mixture effects in less contraction and lower cracking for RCC pavements. Studies have also represented that in a mixture with a steady cement quantity, exsiccate shrinkage reduce as the quantity of rough aggregate enhancement, owing to large constraint [15]

### H. Permeability

The permeability of RCC paving is mainly rely on on the pores in the d RCC and the amount of compaction and porosity of the mixture . so, it is generally influenced by the ration of mixture component, procedure of placement and degree of compaction. hardened Roller Compacted Concrete perhaps a little high penetrable because of voids entrapment

## VIII. RCC MATERAIL CHOICE

### A. Coarse Aggregates

There are some specifications for guidance and advancing for utilization rough aggregate in RCC such as M6/M80, AASHTO. commonly the size of Coarse aggregates are restricted 19 mm to earning a hard and strong surface and to segregation forbidding and reduction. Generally acceptable Nominal Maximum Size of Aggregate (NMSA) change between [ 16 to 19 mm]. NMSAs if if larger than maxomus ize of NMSAs till 38 mm can be utilized and, if accurately ration (if enough fines are available ), can provide a acceptable modality finish. For non-wearing layer or other usage that floor shape is not of more significance greater NMSAs are generally employed. For supply a lower permeable surface, and ameliorate riding caliber, to reduce bleeding and aggregate separation from concrete surface , enhance stickness and bonding , NMSAs lower than. (19 mm) can be applied. Also a it can increment the cement utilization and decrease the stability and resistance of the pavement.

### B. Fine Aggregates

All specification and characteristics and performance of this kind of aggregates must corresponding to ASTM C33. The employed of aggregate portion passing sieve No. 200, that gives high quantity of dust could be appropriate for utilized in RCC if the fines are non-plastic,can aid to decrease the void and pores in RCC mixing. .

## Road Construction by using Rolled Compacted Concrete

A large quantity of fine aggregates lead to decrement of cement and equivalent paste, which, when equity by the suitable proportional with rough and harsh aggregate, supply a mixture that have adequate capacity for compaction and have good performance. To reduce and increment shrinkage clays and silts in RCC aggregates should be prevent because they can increment shrinkage and decrease strength. Fine aggregate approximately 92% to 98% larger than 75  $\mu\text{m}$ . The amount water requirement for mixture, compaction ability, polished and evenness of surface and permanence of the RCC directly related to fine aggregate. Crushed fine aggregates also utilized in RCC since it has more intertwining therefore has more ability for transport and bearing loads. Although rounded fine aggregates can be. [5]

### C. Cementitious Materials

The mixture of RCC can be made with all of the fundamental kinds of hydraulic cement, mingled cements, or a composition of pozzolan dehydraulic cement. A description discourse of the choice and utilization of hydraulic cements and complementary cementitious materials can be obtained in ACI 225R, Guide to the Selection and Use of Hydraulic Cements, and Integrated Materials and Construction Practices for Concrete Pavement: A State-of-the-Practice Manual (IMCP 2007). Generally utilizing binding materials are as following:

#### a. Fly ash

The amount of Cementitious materials is about 11% by mass of concrete in a specific Roller Compacted Concrete mixture for pavement. The fly ash quantity is generally about (20 to 30 %) by mass of the total amount of binder components for typical pavement of highway. Portland cement in Roller Compacted Concrete is partly replaced with Fly ash which provides the fine material quantity in the mixture, fly ash chip in to strength enhancement owing to its pozzolanic characteristic, on the other a partial of sand can be replaced with fly ash. The amount of fly ash can be increased as the existing aggregates do not include sufficient fine materials. [16]

#### b. Blast furnace slag and phospho-gypsum

This type of cementitious materials can increase the time of setting for RCC, therefore permitting an increased time for construction. [17].

#### c. Silica fume

The influence of silica fume is more noticeable when increasing it together with superplasticizer to the mixture of RCC. But when only silica fume is used, the dry density of RCC is not improved. Silica fume quantity to the total binder content should not be more than 10% by mass. The whole quantity of cementitious material be composed of cement and pozzolan - usually simplify as (C + P) - used in the mixture of RCC is commonly in ranging (240 and 360 kg/cubic meter)

#### d. Water and chemical admixtures

Same factors that governed Water modality for normal concrete also control water quality in RCC. American Concrete Institute Committee 214. 2002. Evaluation of Strength Test Results of Concrete. ACI Report 214R-02.

Farmington Hills, MI: American Concrete Institute. Entraining a sufficient quantity of air in to RCC is more arduous, especially with mixtures possessing no quantifiable slump. The air blubber knowledge is sole feasible if enough quantity of water is existing. An air-entraining factor is more effectual as there is adequate water which forms a layer around any bubble. Therefore there is a contestation for water between the solid particles and the bubbles. (American Concrete Institute Committee 325. 2002. Guide for Design of Jointed Concrete Pavements for Streets and Local Roads. ACI Report 325.12R-02. Farmington Hills, MI: American Concrete Institute. Although a set-retarding admixture can also be added in order to permit a retardation of the rolling procedure with the absence of cold joints creation. Although, from permanence point of view utilize of air-entraining agent is compulsory [18].

## IX. MIX DESIGN

Some techniques presently available for proportionate mixes of RCC for pavements; generally, not only one acceptable technique is available. The chief RCC proportionate technique subtends those depend on: 1) the solid suspension model, 2) concrete consistency experiment, 3) soil compaction testing, and 4) the optimal paste volume method. Any method that utilized, the objective is to produce a mixture of RCC has adequate volume of paste needed to cover the aggregates existing in the mix and to accumulate in the gaps among them. [19].

### A. Proportioning by employ Consistency Tests of Concrete

Proportioning techniques that utilized consistency tests of concrete commonly necessary the creation of special mixture criterion -like the aggregate quantity, water quantity, or the quantity of cementitious materials- and then regulate one of the mentioned criteria to obtain a necessary degree of workability, strength, or consistency. By conformance this technique, each component existing in the mixture is capable to optimize to gain the favorable RCC characteristics in both the fresh and hardened states. To distinguish the enough minimum volume of paste, a dynasty of examination mortar mixtures as well as the iteration water to binder and sand to cementitious proportion is get ready and mold, gauged the density of all mixtures. For a specific ratio of water to binder, a certain proportion of sand to cementitious will be obtained at optimized density of mixture. The ratio of water to binder is chosen to gain the indispensable designed strength. After selection the ratio of both water to binder and sand to cementitious, the appropriateness of fine and coarse aggregate should be for achieving desired workability

### B. Proportioning by Utilization of the Solid pendency pattern

The proportioning technique is utilized to clearly describe the portions of all components in arid solid state (silica fume, fly ash, cement, and fine and coarse aggregate) and their arid packing density of a defined mixture of RCC. Using this optimized arid packing density and the each of the dry solid ingredients, authentic computer dramaturgy quantity of water required to completely satisfy for void spaces filling between the arid components. By knowing the characteristics

of a given material such as specific gravity, gradation, and void contents of each arid solid component, authentic computer dramaturgy is capable to be operated by employing this ideal. The great benefit of the solid postponement ideal is to take advantages to recalculate the optimum proportions very fast[16]

### C. Proportioning by Use of the Optimal Paste Volume Method

Originally roller compacted concrete mixes is improved to be used for some large structures as well as dams, lately this method is also utilized for the mixes proportioning of non-air-entrained Roller Compacted Concrete pavement. This method involves three main stages. 1) Selection of aggregate gradation that includes the most possible amount rate of voids for a given condensing energy. 2) The remaining voids amount is utilized to modify the paste volumetric portion so as to achieve the necessitate workability. 3) In this stage, the ratio of W to (C + P) has been selected as well as the proportion of the cement and remaining cementitious materials which are used in the paste manufacturing having sufficient binding capacity to fulfill the requirements of strength for the project (Gagné, R., "Mixture Proportioning of Non-Air-Entrained RCC for Pavements", Concrete International, Vol. 21, No. 5, 1999.

### D. Proportioning by Use of Soil Compaction Tests

This method includes founding a correlation between the moisture content and density of Roller Compacted Concrete mix by condensing samples higher up of moisture contents range as delineated in the "Moisture-Density Relationship" part of this document. Tests of moisture-density conducted and curves of moisture-density are founded over a range of contents of cementitious material. Then the strength test specimens are prepared by compacting them at the optimal moisture content for all cementitious material content. As a result of the mentioned tests, a scheme of strength against the content of cementitious material is founded in the purpose of selection the minimum content of cementitious materials that will have the requirements for the design.

### E. Moisture-Density Relationship

The optimum moisture content and maximum density of RCC mixtures can also be determined by moisture-density test. The most frequent and well-known method for most geotechnical and laboratories testing for materials to carry out is the modified Proctor compaction test (ASTM D 1557). The excess moisture pushes the particles apart as the mix is too wet. For mix design and field quality control we should select the moisture content at which is achieved at maximum density. For strength and durability of RCC density is an important factor, so that the project specifications are required including the minimum level of density. However it should not be less than 98% of the maximum total density. Since the field moisture content will typically not give plenty variety to the maximum, the majority of specifications suggested the necessitated density in conditions of wet or total density. The density in the field usually can be determined through the utilization of a nuclear density gauge. This device measures both the moisture content and the wet density of Roller Compacted Concrete. Moisture content measurement forms a significant role for quality control of RCC since the data is utilized in evaluating the compaction productivity and the behavior of materials; hence, precise moisture determination is crucial in

most specifications references of Roller Compacted Concrete constructions of wet density as a replacement of dry density. [20]

## X. POTENTIAL LIMITATIONS OF RCC

Aware should be taken by the companies and agencies to a potential challenges and limitations associated to pavements constructed with RCC, the followings are some of them:

- The profile and smoothness of RCC without diamond grinding might not be appropriate for pavements bearing traffic with high-speed.
- Comparing to conventional concrete, the amount of RCC that can be mixed in a ready mix truck or in a transit mixer is usually lower, because of the lack of moisture of RCC mixture
- Both adjacent slabs and horizontal lifts have to be placed during a period not more than (60 minutes) to guarantee excellent bonding.
- Compacting the edges of pavement are the most difficult point for RCC, so that the greatest degree of standards specify 96% modified proctor density on cold joints in place of the 98% required on interior pavement sections. History has shown that correctly prepared and consolidated cold joints execute very well
- Because of the comparatively low content of water, RCC paving in hot-weather needs more vigilance to decrease evaporated water .
- Admixture portion can be high for RCC contrast to in place concrete, due to the dryness of the RCC mixture.

## XI. RESULT AND DISCUSSION

The traffic loads and alteration of weather condition are the most important factors that influenced design steps of pavement durability . When RCC, are laying on subbase strong stratum, has more resistance against failure and durability.. The durability of an RCC pavement influenced The predominant climatic status,, season and the timing, during paving processes. High density asphalt paver machine used for paving RCC then compacted by vibration roller .The placing of RCC no need to frame work, , amplify with steel, or finishing of surface. The RCC has more open contexture as can see in asphalt pavement and surface is more open, similar to an asphalt concrete (AC) surface, and mix designs include of analogous aggregate grading , portion and same system of installation. Extrem - density asphalt placement apparatus, These machine gives a large primary denseness in the scope of 90% to 96% and provide slick floor face by small rolling in getting the ending denseness. This type of paver can putlayers from 10 to 22.5 cm thick and lay down lanes breadths from 2.6 to 7.6 m., a main part of the manufacturing of a RCC paving is the rolling action. That generally include of preliminary compaction and finally rolling for finished.

## Road Construction by using Rolled Compacted Concrete

primary compacting often is performed by rooler that has weight of a 10- to 12-ton The aim of rolling system is to attain minimum 98% density. Finish rolling finishing is commonly carry out by a roller that have weight nearly with a 3- to 6-ton roller and can be a compacted by of duplex steel or rubber tired rolling. By the finish rolling can to eliminate roller signs on floor of the concretete. The final surface of RCC paving commonly is not too smooth, since steel- rollers used to compaction the concrete. There are three methods to manufacturing longitudinal joints first Vertical cold joints that has acceptable acting and proficiency since it has not capacity to transmission the loads. The second type joint is of angular cold joint need the utilized of a high- denseness paver. The utmost angle for the joint is nearly 15 degrees. A vibrating tamper can be employed to ameliorate rim performance; if, saw is not employed that supply a low-price method to constructing the longitudinal joint. The abutting lane should be placed as the same time that one lane is finished. The third method to construction joints is Fresh joint, they are paved as they are in asphalt concrete placements

### XII. CONCLUSION

RCC pavement are more merit since it has more acceptable properties such as (low price and economic, safety, more performance and stability). RCC pavements have considerable application in our situation particularly for small traffic road and it can be used as a appropriate discretion to normal concrete road or asphalt roads.. Also, under the same condition, it has lower thickness than flexible pavements require if both of them have the same status . The RCC with supreme strength pavements remove prevalent and costly defects that required high money for treatment associated with asphalt pavements, specially rutting, because RCC pavements will not soften under high temperatures.

### REFERENCES

1. Luhr, David R. "Design and construction of roller-compacted concrete pavements for container terminals." In Ports 2004: Port Development in the Changing World, pp. 1-10. 2004.
2. Vahedifard, Farshid, Mahmoud Nili, and Christopher L. Meehan. "Assessing the effects of supplementary cementitious materials on the performance of low-cement roller compacted concrete pavement." Construction and Building Materials 24, no. 12 (2010): 2528-2535.
3. Harrington, Dale, Fares Abdo, Wayne Adaska, Chetan V. Hazaree, Halil Ceylan, and Fatih Bektas. "Guide for roller-compacted concrete pavements." (2010).
4. Delatte, Norbert. Concrete pavement design, construction, and performance. Crc Press, 2018.
5. Carboneau, Neal. "Roller Compacted Concrete Manual for Local Government Agencies Warren, Ted. "Roller Compacted Concrete for Dam Construction." Volume 22 (2012): 87-90.." (2011).
6. Warren, Ted. "Roller Compacted Concrete for Dam Construction." Volume 22 (2012): 87-90.
7. Marjanović, Milica, Igor Jokačić, and Grad Civil Eng. "APPLICATION OF ROLLER COMPACTED CONCRETE FOR PAVEMENT STRUCTURES."2015
8. Marjanović, Milica, Igor Jokačić, and Grad Civil Eng. "APPLICATION OF ROLLER COMPACTED CONCRETE FOR PAVEMENT STRUCTURES." (2018)
9. Harrington, Dale, Fares Abdo, Wayne Adaska, Chetan V. Hazaree, Halil Ceylan, and Fatih Bektas. "Guide for roller-compacted concrete pavements." (2010).

10. Shin, Kyung Joon, and Neal Carboneau. "The Indiana local technical assistance program roller compacted concrete pavement manual for local government agencies." (2010).
11. Delatte, Norbert. Concrete pavement design, construction, and performance. Crc Press, 2018.
12. Bugaevsky, S. A., S. N. Korzun, A. V. Vinnikov, V. S. Semyonenko, and M. S. Bugaevsky. "ON THE ISSUE OF THE USE OF ROLLER-COMPACTED CEMENT-CONCRETE MIXTURES FOR CONSTRUCTION OF ROAD PAVEMENTS." (2018).
13. Tayabji, Shiraz D., and Paul A. Okamoto. Engineering properties of roller-compacted concrete. No. 1136. 1987.
14. Hazaree, Chetan Vijaysingh. "Transport properties and freeze-thaw resistance of roller compacted concrete (RCC) for pavement applications." (2007).
15. Pittman, David W., and Steven A. Ragan. "Drying shrinkage of roller-compacted concrete for pavement applications." Materials Journal 95, no. 1 (1998): 19-26.
16. Marchand, J., R. Gagné, E. Ouellet, and S. Lepage. "Mixture Proportioning of Roller Compacted Concrete ea Review, pp. 457e487." Concrete Technology Special Publication SP-171e22 (1997).
17. Madhkhan, Morteza, and Arash Aghaeipour. "Effect of ground granulated blast furnace slag (GGBFS) on mechanical properties of roller-compacted concrete pavement." Journal of Testing and Evaluation 48, no. 4 (2018).
18. Piggott, Robert W. Roller-compacted concrete pavements: A Study of Long Term Performance. Portland Cement Association, 1999.
19. American Concrete Institute. ACI manual of concrete practice. ACI, 2013.
20. Astm, D. "1557. Standard test methods for laboratory compaction characteristics of soil using modified effort." West Conshohocken, USA (2012).

### AUTHORS PROFILE

**Muhammad Kh.** Musa.,Ph.D. Students, Civil Engineering Department/ Near East University/ North Cyprus, Nicosia, Via Mersin 10, Turkey , mmkidre@gmail.com

**Hazar M. Nassrullah** .Master Students, Civil Engineering Department/ Near East University/ North Cyprus, Nicosia, Via Mersin 10, Turkey , hazhareng83@yahoo.com