

A Mini Researchon Eco-Friendly Synthesized Nanoparticles and its Applications



Deepthi Pula, R Puviarasi

Abstract: Nanotechnology is emerging technology with its applications in the respective fields. To clear the demands of energy and power there is a need to develop energy systems. This review has details about biological synthesis of nanoparticles and applications. Organic synthesis of nanoparticles may be done using micro organisms or plant extract. Organic synthesis of nanoparticles corresponds to less cost and low toxic in nature. A reducing agent is added to the extract for organic synthesis of nanoparticles. The synthesized particles are sent for many characterization techniques to know shape, size and stability. Nano particles have many applications in their respective fields. Nanotechnology is used in biological and medical fields, agriculture, electronics and chemical fields.

Key words: Green synthesis, plant extract, nanoparticles, applications of nanoparticles.

I. INTRODUCTION

As a whole review it is known that metal oxide nanoparticles have their own priority in science and innovation because of their chemical and physical properties. (1,2). Biological synthesis of nanoparticles have many advantages like they are not harmful and toxic to nature. Organic synthesis of nanoparticles can be done with plant extract (3), micro organisms (4), moulds or yeast (5) and isozymes (6). There is necessary to learn the technologies and confidential things and need to implement in concoction of organic nanoparticles. Organic method is mostly preferred for concoction of nanoparticles due to its low cost and non toxic nature. Organic synthesis may be done by plant extract or from micro organisms like yeast and bacteria.

II. GREEN SYNTHESIS OF NANOPARTICLES:

Tin oxide (SnO_2 Np's)

Organic concoction of tin oxide nanoparticles is done by Persia Americana seed methanolic extract by calcining stannous chloride precursors. This synthesized under temperature 300–500 °C. 80ml of stannous chloride solution and methanolic extract of Avocado are heated at 600°C continuously.

The synthesized particles are subjected to many techniques like XRD, SEM and EDAX. SnO_2 nanoparticles synthesized by Persia Americana seed methanolic extract are non toxic and less cost. One of the important application by this synthesis is degrading toxic organic dyes (phenol red). SnO_2 NPs was in the size of 4 nm in range. (7).

Silver (Ag Np's)

Silver nanoparticles have intensive research owing to their wide applications many areas. Silver nanoparticles exhibit improved properties based on the shape, size and stability. Silver nanoparticles are synthesized by using carob plant extract. In the process of synthesis reduction of Ag^+ ions to Ag nanoparticles from silver nitrate solution within 2 min of reaction time at ambient temperature is done. By the completion of this process the solution becomes black. This mixture is centrifuged and washed with distilled water and ethanol. Synthesized nanoparticles are sent for characterization techniques like XRD, UV–vis spectroscopy, SEM. The techniques states that nanoparticles are of size 5 to 40 nm with an average size as 18 nm. (8) By this synthesis antibacterial activity of biologically synthesized silver nanoparticles was evaluated against E. Coli pathogen. (9)

Iron (Fe Np's)

Green synthesis of iron nanoparticles can be done by various tea extracts. This has been recently proposed to reduce cost and environmental friendly. Organic synthesis is preferred instead of physical and chemical methods to make non toxic to nature. (10,11,12) Organic synthesis of iron nanoparticles by tea extracts used for degrading bromothymol blue by Fenton oxidation. The initial concentrations of tea extracts are prepared by heating them at room temperature. These extracts are vacuum filtered and $FeSO_4$ solution is added to the extract. The stock solution further obtained was diluted using deionized water. The synthesized nanoparticles were characterized through UV-vis, SEM, EDS, BET-N₂ and XRD techniques.

Titanium dioxide (TiO_2 Np's)

Among many metal oxide nanoparticles titanium dioxide nanoparticles have wide application in air and water purification due to their potential oxidation strength, stability, nontoxic. Titanium nanoparticles have some specific properties such as optical, catalytic photo catalyst, photo stability which involves in the industrial application like pigments and filters. (13,14) Titanium nanoparticles are synthesized from titanium isopropoxide solution using nyctanthes leaves extract.

Revised Manuscript Received on October 30, 2019.

* Correspondence Author

Deepthi Pula*, ECE dept, Saveetha school of engineering, SIMATS, Chennai, Tamilnadu, India.

R Puviarasi, Assistant professor, ECE dept, Saveetha School of Engineering, SIMATS, Chennai, Tamilnadu, India.

© The Authors. Published by Blue Eyes Intelligence Engineering and Sciences Publication (BEIESP). This is an open access article under the CC-BY-NC-ND license <http://creativecommons.org/licenses/by-nc-nd/4.0/>

A Mini Researchon Eco-Friendly Synthesized Nanoparticles and its Applications

The synthesized nanoparticles are subjected to many characterization techniques such as XRD,SEM,PSA.Titanium dioxide nanoparticle ranges from 100 to 150nm.

III. CHARACTERIZATION TECHIQUES

After the synthesis of nanoparticles,to confirm the detailed review onsize,shape,stability and properties of particle, particle is gone through various characterization techniques.The common techniques in characterization techniques of nanoparticles are UV Vis absorption spectroscopy,Xraydiffraction,energy dispersive Xrayanalysis,scanning electron microscopy and transmission electron microscopy etc.,

UV Vis absorption spectroscopy is used to check how much big it is and to know external form of nanoparticle in water combined solution. (15) Xraydiffraction gives the status about similraities of a particle,size and appearance confirmation of metallic nanoparticles(16).Scanning electron microscope is one of the characterization technique which produces images of sample by scannind the phase of particles.

IV. APPLICATIONS OF NANOPARTICLES& RESULTS

In the past few there is a dramatic increase in the publication of nanotechnology.Organic engineering which refers to the formation of organic nanoparticles and then these products are used in many fields for their development.Green synthesis of nanoparticles have their effective use in healing,therapeuticapplications and analysis applications (17,18,19, 20).

Nanoparticles have many applications in biomedical field such as imaging nad drug delivery.Organic synthesis nanoparticles are used to remove pollutants in nature.Nanoparticles are used in industries to protect wood,plastic and textiles.Nanoparticles have many commercial applications.Nanoparticles have different applications with respect to the type of nanoparticle used.

V. CONCLUSION

Organic synthesis of nanoparticles have move out of as an preferable technology among all the technologies.Green synthesis of nanoparticles increases economic viability and property management.Biological synthesis of nanoparticles are inexpensive and free from chemical products for their usage in biological applications.Biological methods do not need any chemical substances.The waste of plants or fruits are non toxic and can be easily disposed.Nanoparticles synthesized by organic method have more firmness than compared with the nanoparticles synthesized from physical or chemical methods.There are huge applications using organic synthesized nanoparticles as discussed.

REFERENCES

1. Ruchitha G. Effects of diluted ethylene glycol as a fruit-ripening agent. *Global J Biotechnol Biochem* 2008;3:8-13.
2. Anwar R, Malik AU, Amin M, Jabbar A, Saleem BA. Packaging material and ripening methods affect mango fruit quality. *Int J Agric Biol* 2008;???:1814-9596.

3. Xiaodi Guo, Lianying Wang, Shuang Yue, Dongyang Wang, Yanluo Lu, Yufei Song, and Jing He . Single-Crystalline Organic–Inorganic Layered Cobalt Hydroxide Nanofibers: Facile Synthesis, Characterization, and Reversible Water-Induced Structural Conversion. *Inorganic Chemistry* 2014, 53 (24) , 12841-12847. DOI: 10.1021/ic501812n
4. Dongniu Wang, Xifei Li, Jiajun Wang, Jinli Yang, Dongsheng Geng, Ruying Li, Mei Cai, Tsun-Kong Sham, and Xueliang Sun . Defect-Rich Crystalline SnO2 Immobilized on Graphene Nanosheets with Enhanced Cycle Performance for Li Ion Batteries. *The Journal of Physical Chemistry C* 2012, 116 (42) , 22149-22156. DOI: 10.1021/jp306041y
5. Marappan Sathish, Satoshi Mitani, Takaaki Tomai, and Itaru Honma . Ultrathin SnS2 Nanoparticles on Graphene Nanosheets: Synthesis, Characterization, and Li-Ion Storage Applications. *The Journal of Physical Chemistry C* 2012, 116 (23) , 12475-12481. DOI: 10.1021/jp303121n
6. Marappan Sathish, Satoshi Mitani, Takaaki Tomai, and Itaru Honma . Ultrathin SnS2 Nanoparticles on Graphene Nanosheets: Synthesis, Characterization, and Li-Ion Storage Applications. *The Journal of Physical Chemistry C* 2012, 116 (23) , 12475-12481. DOI: 10.1021/jp303121n
7. Rute André, Muhammed Nawaz Tahir, Heinz Christoph C. Schröder, Werner E.G. Müller, and Wolfgang Tremel . Enzymatic Synthesis and Surface Deposition of Tin Dioxide using Silicatein- α . *Chemistry of Materials* 2011, 23 (24) , 5358-5365. DOI: 10.1021/cm201977c.
8. Ling Yan Liang, Zhi Min Liu, Hong Tao Cao and Xiao Qin Pan . Microstructural, Optical, and Electrical Properties of SnO Thin Films Prepared on Quartz via a Two-Step Method. *ACS Applied Materials & Interfaces* 2010, 2 (4) , 1060-1065. DOI: 10.1021/am900838z
9. Yu-Fen Wang, Bing-Xin Lei, Yuan-Fang Hou, Wen-Xia Zhao, Chao-Lun Liang, Cheng-Yong Su and Dai-Bin Kuang . Facile Fabrication of Hierarchical SnO2 Microspheres Film on Transparent FTO Glass. *Inorganic Chemistry* 2010, 49 (4) , 1679-1686. DOI: 10.1021/ic902092e
10. Stejskal V, Hudecek R, Stejskal J, Sterzl I. Diagnosis and treatment of metal-induced side-effects. *Neuro Endocrinol Lett* 2006;27 Suppl 1:1-16.
11. Liu YQ, Majetich SA, Tilton RD, Sholl DS, Lowry GV. TCE dechlorination rates, pathways, and efficiency of nanoscale iron particles with different properties. *Environ. Sci. Technol.* 2005;39:1338–1345
12. Liu YQ, Lowry GV. Effect of particle age (Fe-o content) and solution pH on NZVI reactivity: H-2 evolution and TCE dechlorination. *Environ. Sci. Technol.* 2006;40:6085–6090
13. Thompson JM, Chisholm BJ, Bezbaruah AN. Reductive dechlorination of chloroacetanilide herbicide (Alachlor) using zero-valent iron nanoparticles. *Environ. Eng. Sci.* 2010;27:227–232.
14. Lu AH, Salabas EL, Schuth F. Magnetic nanoparticles: synthesis, protection, functionalization, and application. *Angew. Chem. Int. Ed.* 2007;46:1222–1244
15. He F, Zhao D, Liu J, Roberts CB. Stabilization of Fe-Pd nanoparticles with sodium carboxymethyl cellulose for enhanced transport and dechlorination of trichloroethylene in soil and groundwater. *Ind. Eng. Chem. Res.* 2007;46:29–34
16. He F, Zhao D. Hydrodechlorination of trichloroethene using stabilized Fe-Pd nanoparticles: Reaction mechanism and effects of stabilizers, catalysts and reaction conditions. *Appl. Cat. B-Environmental.* 2008;84:533–540
17. Zheng T, Zhan J, He J, Day C, Lu Y, McPherson GL, Piringner G, John VT. Reactivity characteristics of nanoscale zerovalent iron-silica composites for trichloroethylene remediation. *Environ. Sci. Technol.* 2008;42:4494–4499
18. Huang Q, Shi X, Pinto RA, Petersen EJ, Weber J. Tunable synthesis and immobilization of zero-valent iron nanoparticles for environmental applications. *Environ. Sci. Technol.* 2008;42:8884–8889.
19. Smuleac V, Bachas LG, Bhattacharyya D. Aqueous-phase synthesis of PAA in PVDF membrane pores for nanoparticle synthesis and dichlorobiphenyl degradation. *J. Membr. Sci.* 2010;346:310–317.
20. Nadagouda MN, Hoag G, Collins J, Varma RS. Green synthesis of Au nanostructures at room temperature using biodegradable plant surfactants. *Cryst. Growth Des.* 2009;9:4979–4983.